

Effect of SDF application on the bond strength of two different types of composites, used in the restoration of carious primary molars - An in vitro study

¹Manisha Tyagi, Dental Officer, ECHS Poly Clinic, Baghpat.

²Akanksha Tyagi, Senior Lecturer, Subharti Dental College & Hospital, Meerut.

³Ratika Gupta, Senior Lecturer, Inderprastha Dental College and Hospital, Sahibabad, Ghaziabad.

⁴Elizabeth Moirangthem, Senior Lecturer, Rajasthan Dental College & Research Center.

⁵Deepesh Srivastava, Senior lecturer, Inderprastha Dental College and Hospital, Sahibabad, Ghaziabad.

⁶Aadesh Kumar Tomer, Ex. Lecturer, Inderprastha Dental College and Hospital.

Corresponding Author: Manisha Tyagi, Dental Officer, ECHS Poly Clinic, Baghpat.

Citation of this Article: Manisha Tyagi, Akanksha Tyagi, Ratika Gupta, Elizabeth Moirangthem, Deepesh Srivastava, Aadesh Kumar Tomer, “Effect of SDF application on the bond strength of two different types of composites, used in the restoration of carious primary molars - An in vitro study”, IJDSIR- April - 2022, Vol. – 5, Issue - 2, P. No. 78 – 83.

Copyright: © 2022, Manisha Tyagi, et al. This is an open access journal and article distributed under the terms of the creative commons attribution noncommercial License. Which allows others to remix, tweak, and build upon the work non-commercially, as long as appropriate credit is given and the new creations are licensed under the identical terms.

Type of Publication: Original Research Article

Conflicts of Interest: Nil

Abstract

Introduction: SDF has been proven as a viable treatment option to arrest caries in young uncooperative patients with high risk. However, to overcome its demerits like black discoloration and restoring the cavity is a big challenge. To mask the discoloration, GIC and composites have been used as intra-coronal restorations in restoring such teeth with varying degree of success. However, its effect on bond strength is still not clear.

Aim: The study aims to evaluate the bond strength of composite restoration on teeth treated with and without SDF using universal testing machine.

Methods: 80 extracted carious primary molars were randomly divided into four groups on the basis of methods of their restoration- Group 1 SDF application followed by Nano composite restoration, Group 2 SDF

application followed by Hybrid composite restoration, Group 3 Hand excavation before Nano composite restoration, Group 4 Hand excavation followed by Hybrid composite restoration.

Result: Nano composite restoration after hand excavation showed statistically significant bond strength than SDF application after Nano composite.

Conclusion: Application of SDF before restoration with Nano composite did not show improved fracture strength.

Keywords: Silver diamine fluoride, composite restoration, hand excavation, carious primary teeth, ECC

Introduction

Dental caries is widely prevalent globally but the distribution and severity of dental caries varies across countries and regions. According to Global Oral Health

Data Bank, prevalence of dental caries varies from 49% to 83% across different countries.¹

More than 40% of the children in India have shown dental caries in both primary and permanent teeth in the past 15 years¹.

Preventive measures such as fluoride gel and varnishes have been in use since ages but unfortunately have not contributed in the decrease of dental caries to a larger extent. On the other hand, a recent material known as Silver Diamine Fluoride (SDF) has proved to have a superior edge.

SDF halts the caries progression and promote caries arrest. It is unique in both killing the bacteria and hardening the teeth It is usually recommended for children with a high risk of developing caries and those living in poor conditions with low socio-economic status.² SDF can also serve as an alternative approach to the conventional restorative treatment in young children who are uncooperative and where any other preventive and therapeutic treatment cannot be carried out. It is a cost-effective treatment for arresting cavitated carious lesions in the most patient friendly way. Thus, the interest in the use of silver diamine fluoride has been growing.

However, it has a major drawback of black discoloration and it is a big challenge to overcome this and restore the cavity. Therefore, GIC and composites have been used as intra-coronal restorations to restore such teeth with varying degree of success. The objective of adhesive dentistry is to establish an effective adhesion of dental material with teeth. Nano and hybrid composite materials have proved their efficacy so far in dentistry.

However, there are hardly any study which compared the bond strength of nano and hybrid composites on the restoration of carious primary teeth after SDF application. Thus, the aim of this in vitro study was to

evaluate the bond strength of teeth treated with and without SDF followed by composite (nano & hybrid) restorations.

Methodology

In this in vitro experimental study, eighty freshly extracted carious primary molar teeth were taken.

Inclusion criteria

- Carious primary molars with at least two surface involvements and minimum of one-third of root remaining

Exclusion criteria

- Single surface carious teeth
- Non-restorable teeth
- Teeth with coronal perforations were excluded from the study.

Procedure

The extracted teeth were stored in 10% formalin. Based on random allocation, teeth were then randomly divided into four groups which consisted of 20 teeth each.

In group I, 38% SDF (Kids-E-Crown, kids-e-dental Llp, Mumbai) was applied on 20 extracted primary molars as per manufacturer's instructions, they were air dried for 1 minute and then they were acid etched with 37% orthophosphoric acid for 15 seconds, washed with water and then dried. The bonding agent (VI generation; 3M ESPE) was applied and cured for 10 seconds according to manufacturer's instructions. Teeth were then restored with Nano composite (3M ESPE) restoration.

In group II, 38% SDF was applied on 20 extracted primary molars, they were air dried for 1 minute followed by Hybrid composite (3M ESPE) restoration.

In group III, hand excavation was done of 20 extracted primary molars and then they were restored with Nano composite restoration

In group IV hand excavation was done of 20 extracted primary molars followed by Hybrid composite restoration (figure 1).




Figure 1: Methodology

After the composite restorations, teeth were embedded in acrylic resin block. They were then fixed to universal testing machine and forces were applied at a speed of 1 mm/min at 30 degrees angle till the restoration fractured from the teeth (figure 2).




Figure 2: Sample fixed to universal testing machine

All the readings were noted and the data was statistically analysed using independent/ unpaired t-test keeping 0.05 p value as statistically significant under Statistical Package for Social Science (SPSS version 20.0) software.

Results

The mean value of force at which the restorations debonded from the tooth for each group are shown in table 1.

Group	Mean	Standard deviation
I	209.902	33.92264
II	181.628	50.75977
III	252.659	73.22193
IV	226.232	70.09535

Table 1: Mean value of each group

The mean value was highest in the group III (252.659 N) where hand excavation was done followed by nano composite restoration and it was least in group II (181.628 N) where SDF was applied followed by hybrid composite restoration (figure 3).




Figure 3: Graphical representation of mean values of each group

When group I was compared to group II (table 2), the value of mean force to dislodge the restoration was 195.76 N which was non-significant ($p=0.16$). Insignificant difference was found ($p=0.11$) when group I was compared to group III, where mean value of force was 231.28 N. Similarly, when group I was compared to group IV, p value was 0.51 which was non-significant. Interestingly, when group II was compared to group III mean value of force was 217.14 N and p value was 0.02, which showed significant difference. When group II was compared to group IV and group III was compared to group IV again result was non-significant ($p>0.05$).

Groups	Std. Error Mean	Std. Deviation	Mean	P value
I-II	19.30	43.17	195.76	0.16
I-III	25.51	57.06	231.28	0.11
I-IV	24.62	55.06	218.06	0.51
II-III	28.17	63.00	217.14	0.02
II-IV	27.36	61.19	203.93	0.12
III-IV	32.05	71.67	239.45	0.42

Table 2: Group comparison of mean values

Discussion

Silver compounds, especially silver nitrate, have been used in medicine to control infections for more than a century³. In dentistry, use of silver nitrate is well documented for caries inhibition⁴. There was an old custom in Japan where ladies used to dye their teeth black for expressing their status as married. Though it was regarded as a tooth cosmetic, it had anti caries activity. This practice of dyeing teeth was abolished by the beginning 20th century³. Before the twentieth century, silver nitrate was firmly entrenched in the profession as a remedy for “hypersensitivity of dentin, erosion, pyorrhea, as a sterilizing agent and caries inhibitor in deciduous as well as in permanent teeth⁵. The relationship of fluorides and caries prevention had already been well-established through epidemiologic observations, chemical studies, animal experiments, and clinical trials beginning in the early decades of the twentieth century. Dr Nishino and Yamaga in Japan pioneered the use of ammoniacal silver fluoride for the arrest of dental caries⁶ and developed it to combine the actions of F and Ag which led to the approval for the first SDF product, Saforide (Bee Brand Medico Dental Co, Ltd, Osaka, Japan) in 1970⁷.

SDF has emerged as a boon to pediatric dentistry as a preventive measure. However, the only disadvantage of using SDF is the black staining caused to the tooth structure. Thus, esthetic restorations are needed to overcome this drawback of SDF staining. Various

studies have already showed the success rate of GIC after the pre-treatment of dentin with SDF.

But with a general trend towards the increased preservation of healthy, natural tooth structure and increased demand for aesthetics, the concept of bonding to tooth structure has led to major modifications in cavity preparation and restorative material choice. Thus, composite restoration is the most commonly used restorative material used in clinics due to its high aesthetics and strength.

Enamel consists of 96% inorganic material (Hydroxyapatite), only a small amount of organic matter and 4% H₂O. In oral environment, the organic pellicle covers the enamel surface reducing the surface energy of enamel to 28 dynes / cm, which creates a complex surface for bonding⁸. This enamel surface is cut during cavity preparation which removes the organic pellicle but it does not increase the surface energy. Thus, to increase the surface energy from 28 to 72 dynes/cm etching is required which creates a more homogeneous structure with higher inorganic content and higher surface energy rendering enamel a more predictable structure for bonding. Dentin on the other hand is composed of 65-90% of inorganic content and 30-35% of organic content which makes bonding less predictable compared to enamel.⁸ In order to avoid this problem dentin bonding agents have been introduced in the field of dentistry.

It has also been noted that hydrofluoric acid generally has a detrimental effect on resin bond strength to dentin. Etching with phosphoric acid after exposure to hydrofluoric acid tends to result in higher bond strengths⁹.

In a laboratory study by May et al¹⁰ to investigate the use of 38% silver diamine fluoride (SDF) as a treatment for preventing secondary caries in glass ionomer cement

(GIC) and composite resin (CR) restorations, it was seen that conditioning with 38% SDF increased the resistance of the glass ionomer cement and composite resin restorations to secondary caries. The authors also concluded that at a concentration of 38%, SDF can be incorporated into restorative therapy to improve the success rate of direct restorations in terms of longevity.

SDF reacts with the tooth mineral hydroxyapatite to release calcium fluoride and silver phosphate which are responsible for the prevention and hardening of dental caries.

Since in uncooperative and especially abled children the success of traditional restorative treatment is difficult to achieve. Thus, this in vitro trial was attempted to check whether the bond strength was altered after SDF application or not.

The result of this study suggests that there was insignificant difference in terms of bonding between nano and hybrid composite restorations both when SDF and hand excavation was done. This could be justified by the fact that the bonding is not altered by the type of restoration, but the bonding agent and its penetration into the dentinal tissues are more viable responsible factors.

Furthermore, the results of this study also showed that there was an insignificant difference between SDF and hand excavation irrespective of the type of composite restoration used. It was observed that though SDF did not adversely affect the bond strength of composite restorations but it was reduced; however, these differences were statistically insignificant. The possible reason for this may either be that micro tags are not formed or that SDF might have interfered with their formation. However, SDF seems to offer the ability to chemically control or eliminate the spread of the disease in a frank cavity. This property may reduce the need to

use a hand piece or hand instrument to mechanically remove highly infected dentin. Though there was significant difference between group II & III, which can be due to the variable sample selection or error during sample selection.

Similar results were shown by Uchil¹¹ et al, that the application of SDF with or without acid etching does not affect the bond strength of resin-modified GIC to carious dentin of primary teeth.

However, a contradictory statement was given by Fröhlic¹² et al in a systematic review, that the prior application of silver diamine fluoride significantly decreased the bond strength of composite restorations.

Thus, the result of the present study suggests that the pre-treatment with SDF irrespective of caries excavation may be considered for uncooperative and especially abled children as it does not interfere with the bonding of either nano or hybrid composite to carious dentin in primary teeth.

Conclusion

Within the limitations of this study, it can be concluded that

- SDF did reduce bond strength of composite restorations; however, these differences were statistically insignificant.
- Bond strength of Nano composite restorations following hand excavation was highest whereas restorations with hybrid composite following SDF application showed least bond strength.
- Bond strength is not much affected, if caries is not excavated properly. The observed bond strength of each group was in descending order as group III > group IV > group I > group II.
- Thus, pre-treatment with SDF irrespective of caries excavation may be considered as a potential treatment protocol for uncooperative and especially abled children.

References

1. Frencken JE, Sharma P, Stenhouse L, Green D, Lavery D, Dietrich T. Global epidemiology of dental caries and severe periodontitis – a comprehensive review. *J Clin Periodontol.* 2017;94–105.
2. Zhao IS, Gao SS, Hiraishi N, Burrow MF, Duangthip D, Mei ML, Lo EC, Chu CH. Mechanisms of silver diamine fluoride on arresting caries: a literature review. *Int Dent J.* 2018;68(2):67-76.
3. Rajendran R, Shiva Patha sun Dharam B, Raghu AR. *Shafer's Textbook of Oral Pathology.* In: Shafer, Hine, Levy, editors. 6th ed. Noida, India: Elsevier; 2005.
4. Kundu H, Patthi B, Singla A, Jankiram C, Jain S, Singh K. Dental Caries Scenario Among 5, 12 and 15-Year-old Children in India- A Retrospective Analysis. *J Clin Diagn Res.* 2015;9(7)
5. Khan M, Qureshi A. Prevalence of Dental Caries among Slum Dwelling Children Aged 12-15 Years in Kolhapur, Maharashtra, India, *International Healthcare Research Journal.* 2018; 2(1)
6. Jackson SL, Vann WF, Kotch JB, Pahel BT, Lee JY. Impact of poor oral health on children's school attendance and performance. *Am J Public Health.* 2011;101(10):1900-6.
7. Weintraub JA, Ramos-Gomez F, Jue B. Fluoride varnish efficacy in preventing early childhood caries. *J Dent Res.* 2006;85(2):172–6.
8. Kumar, J.S. & Jayalakshmi, S. Bond failure and its prevention in composite restoration – A Review. 2016; 8:627-631.
9. Sundfeld Daniel, Palialol Alan Rodrigo Muniz, Fugolin Ana Paula Piovesan, Ambrosano Gláucia Maria Bovi, Correr-Sobrinho Lourenço, Martins Luis Roberto Marcondes et al. The effect of hydrofluoric acid and resin cement formulation on the bond strength to lithium disilicate ceramic. *Braz. oral res.* 2018; 32: 43.
10. Mei ML, Zhao IS, Ito L, Lo EC, Chu CH. Prevention of secondary caries by silver diamine fluoride. *Int Dent J.* 2016;66(2):71-7
11. Uchil SR, Suprabha BS, Suman E, Shenoy R, Natarajan S, Rao A. Effect of three silver diamine fluoride application protocols on the micro tensile bond strength of resin-modified glass ionomer cement to carious dentin in primary teeth. *J Indian Soc Pedod Prev Dent* 2020; 38:138-44
12. Fröhlich TT, Rocha RO, Bottom G. Does previous application of silver diamine fluoride influence the bond strength of glass ionomer cement and adhesive systems to dentin? Systematic review and meta-analysis. *Int J Paediatr Dent.* 2020;30(1):85-95.